



(19)

(11) Publication number:

0'

Generated Document.

PATENT ABSTRACTS OF JAPAN

(21) Application number: **05244178**(51) Intl. Cl.: **C23C 14/06 B23B 27/14 B23**
15/01 C22C 29/16 C23C 16/3(22) Application date: **30.09.93**

<p>(30) Priority:</p> <p>(43) Date of application publication: 11.04.95</p> <p>(84) Designated contracting states:</p>	<p>(71) Applicant: SUMITOMO ELECTRIC</p> <p>(72) Inventor: FUKUI HARUYO NAKAYAMA AKIRA SETOYAMA MAKOTO YOSHIOKA TAKESHI YAMAGATA KAZUO</p> <p>(74) Representative:</p>
---	--


(54) ULTRA-THIN FILM LAMINATE

(57) Abstract:

PURPOSE: To improve the wear resistance and oxidation resistance of the surface of a substrate by alternately repetitively laminating thin films of two kinds of Ti-Al-N compds. varying in compsn. on the surface of the substrate.

CONSTITUTION: The thin film 3 which consists of carbides, nitride and carbonitrides of group IVa, Va and VIa metals in periodic table and has a thickness of 0.05 to 5 μ m is formed by an ion plating method by a vacuum arc discharge on the surface of the hard base material 2, such as cutting tip, drill or end mill, consisting of a WC-base sintered hard way, cermet, ceramics or high-speed steel, Two kinds of the compds. A, B expressed by $Ti_xAl_{1-x}N$ (where $0 \leq x < 0.5$) and $Ti_yAl_{1-y}N$

(where $0.5 < y \leq 1$) are alternately laminated in many layers on the surface of the thin-film layer 3 by setting the sum λ of the thickness t_1 , t_2 of these compds. as a repetitive lamination period of 0.5 to 20nm. The thin films 1 having the total thickness of 0.5 to 10 μ m are thus formed. The wear resistance and oxidation resistance of the substrate 1 are greatly improved by the alternately laminated thin films of the Ti-Al-N alloy.



COPYRIGHT: (C)1995,JPO

